

**IN THE CLAIMS**

Please amend claim 6 as follows:

**Claims 1-5 (Canceled).**

**Claim 6 (Currently Amended):** A radical copolymerizable unsaturated resin composition comprising

a compatibilizing agent,

an addition polymerized polymer (D) for low profile,

a radical copolymerizable unsaturated resin, and

a polymerizable unsaturated monomer,

wherein the compatibilizing agent is a graft copolymer (A) which contains styrene repeat units as a principal component, said graft copolymer (A) having:

a principal chain (A1) that is a copolymer comprising (meth)acrylate repeat units and the styrene repeat units; and

a side chain (A2) selected from a ring-opening polymerized polyether side chain consisting of a polyoxyalkylene ether, a polyester side chain, and a polycarbonate side chain,

the side chain (A2) being bonded to the principal chain (A1),

the weight ratio (A1/A2) of a principal chain (A1) to a side chain (A2) is within a range of ~~70/30-30/70~~ 65/35-20/80, and

the amount of the graft copolymer (A) being within a range of 0.1-10 parts by weight based on the total of the amount of the radical copolymerizable unsaturated resin and the amount of the addition polymerized polymer as 100 parts by weight.

**Claim 7 (Canceled).**

**Claim 8 (Previously Presented):** A radical copolymerizable unsaturated resin composition according to claim 6, wherein the radical copolymerizable unsaturated resin is an unsaturated polyester.

**Claim 9 (Previously Presented):** A molding material comprising the radical copolymerizable unsaturated resin composition of claim 6.

**Claim 10 (Original):** A molded article comprising the molding material of claim 9.

**Claim 11 (Previously Presented):** A radical copolymerizable unsaturated resin composition according to claim 6, wherein the radical copolymerizable unsaturated resin is an unsaturated polyester.

**Claim 12 (Previously Presented):** A radical copolymerizable unsaturated resin composition according to claim 6, wherein the principal chain (A1) comprises 70-99.9% by weight of the styrene repeat units and 0.1-30% by weight of other unsaturated repeat units including the (meth)acrylate repeat units.

**Claim 13 (Previously Presented):** A radical copolymerizable unsaturated resin composition according to claim 6, wherein the side chain (A2) comprises oxyethylene units in an amount within a range of 60-100% by weight.

**Claim 14 (Canceled).**

**Claim 15 (Previously Presented):** A radical copolymerizable unsaturated resin composition according to claim 6, wherein the amount of the graft copolymer (A) is within a range of 0.5-3 parts by weight based on the total of the amount of the radical copolymerizable unsaturated resin and the amount of the addition polymerized polymer as 100 parts by weight.